

# B 270™ Flat Glass

To meet a variety of different market demands, SCHOTT offers its well-known B 270™ crown glass in sheet glass form. B 270™, manufactured by the up-drawn method, offers high stability with respect to solarization in combination with high transmission in the visible wavelength range. It has a fire-polished surface and high chemical stability. B 270™ is available in a wide range of thicknesses, a variety of in-stock sizes and shapes, and custom shapes. It can also be custom processed upon request.



## Applications




### CD / DVD Pick up Digital Projection

- High transmittance
- Cost efficient processing due to wide thickness range




### CRT Door Phone

- High solarization stability
- Fire-polished surface for use without polishing



### Surface acoustic wave type touch panel

- Low acoustic attenuation
- High transmittance



### Monitor glass for coaters

- High transmittance
- Cost efficient process monitoring



### Gifts

- High transmittance
- Crystal like appearance
- Fusible with adapted glasses

## Technical Data

Dimensions	406 mm x 258 mm, 840 mm x 800-920 mm, 1680 mm x 800-920 mm (16.0 in x 10.1, 33 in x 31.5-36.2 in, 66.1 in x 31.5-36.2 in) other formats upon request
Thicknesses	0.8 mm up to 17.0 mm < 0.8 mm on request
Luminous transmittance $T_{VD65}$ (d = 2.0 mm)	91.7 %
Coefficient of mean linear thermal expansion $\alpha$ (20 °C; 300 °C) (static measurement)	$9.4 \cdot 10^{-6} \text{ K}^{-1}$
Transformation temperature $T_g$	533 °C
Dielectric constant $\epsilon_r$ at 1MHz	7.0
Refractive index $n_D$	1.5229
Density $\rho$	2.55 g/cm <sup>3</sup>

Advanced Materials  
**SCHOTT AG**  
 Hüttenstraße 1  
 31073 Grünplan  
 Germany

Phone +49 (0)5187/771-204 or -746  
 Fax +49 (0)3641/2847-429  
 info.thinglass@schott.com  
 www.schott.com/advanced\_materials

**SCHOTT**  
 glass made of ideas